



**Standard Specification for Architectural Cast Stone**

**Client:**

Company Name      Precast Stones NY Corp  
Reported To        Wilson Gordillo  
Company Address    3275 Grace Avenue, Bronx, NY, 10469  
Facility Location    3275 Grace Avenue, Bronx, NY, 10469  
Project                13135 Precast Stones NY Corp  
Report Notes        3/20/23

**Samples:**

**Chain of Custody**    **Client-ID**   **ATG-ID**   **Description**  
COC-032923-13135-01   Concrete   5569-1   3/20/23 Concrete Block

**Smpl. By**   **Sampled**   **Recv. By**   **Received Method**   **Condition Store**  
Client        3/20/23    RQ        3/29/23   Random   Intact    Amb.

**Photo:**

5569-1 Concrete 3/20/23 Concrete Block



**Notes:**

1. Equip No. / Calib: Balance (702) - 3/31/24; Caliper 6" (3) - 1/24/24; Thermometer - Concrete (Lab Casting) (2093) - 8/23/23;
2. Technician Quals: C1194 - 1/3/28; C1195 - 1/3/28; C1364 - 1/3/28;
3. Chain of Custody on file.
4. Test Notes/Spec: Per Client / Standard(s) for applicable material(s).
5. Abbreviations: C=Conforms to Spec value shown, NC=Non-Conformance to Spec value shown, R=Report for Information only, NR=Not Requested by Client/Contract. Also see <https://dms.appliedtesting.com/Download/abbreviations.pdf>

END-OF-REPORT

**Test Results:**

ASTM	Description	Spec	Result	Units	C/NC
C1194	Avg. Comp. Strength (28 day)	≥6,500	10,065	psi	C
C1194	Comp. Strength Test Age	N/A	28	days	R
C1195	Avg. Absorption	≤6	4.3	%	C
C1195	Absorption Test Age	N/A	28	days	R

**Statement of Conformity:**

Tests (assigned C) conform to the referenced Spec value shown.

Test Date (Start - End): 3/29/23 - 4/17/23

TS Technician:                      Ryan A. Quitinsky

TS Manager:                         Thomas C. Smith

6. Report may be reproduced or distributed only in its entirety.
7. Interpretation of test results is beyond the scope of this report.
8. Results apply to samples as received. Description per client.
9. Significance and use of test results per ASTM Standard.
10. Precision and bias of test results per ASTM Standard.
11. Test Location: 401 E. 4th St, Bridgeport PA 19405.
12. Decision Rule - Simple acceptance used in conformance decisions. Guardband (w) set equal to zero (0). (No application of measurement uncertainty).